

**Amendments to the Claims:**

This listing of claims will replace all prior versions and listing of claims in this application.

**Listing of Claims:**

Claims 1-19 (Canceled).

20. (Currently Amended) A process to polymerize olefins comprising contacting, in a polymerization system, olefin monomers having three or more carbon atoms with:

- 1) a metallocene catalyst compound,
- 2) an activator,
- 3) optionally comonomer, and
- 4) optionally diluent or solvent,

at a temperature above the cloud point temperature of the polymerization system and a pressure no lower than 10 MPa below the cloud point pressure of the polymerization system and less than 1000MPa,

where the polymerization system comprises the monomers, any comonomer present, any diluent or solvent present, and the polymer product, and

where the olefin monomers are present in the polymerization system at 40 weight % or more, and

where polymerization takes place in a loop reactor operated at pressures of 25 to 30 MPa.

21. (Canceled)

22. (Original) The process of claim 20 where the temperature is between 140 to 180°C.

23. (Canceled)

24. (Original) The process of claim 20 wherein the pressure of the polymerization system is above the cloud point pressure of the polymerization system.

Claims 25-26 (Canceled)

27. (Original) The process of claim 20 wherein solvent and or diluent is present in the

polymerization system at 0 to 25 wt %.

28. (Original) The process of claim 20 wherein solvent and or diluent is present in the polymerization system at 0 to 10 wt %.

29. (Original) The process of claim 20 wherein the olefin monomers having three or more carbon atoms are present in the polymerization system at 55 wt % or more.

30. (Original) The process of claim 20 wherein the olefin monomers having three or more carbon atoms are present in the polymerization system at 75 wt % or more.

31. (Original) The process of claim 20 wherein the olefin monomer having three or more carbon atoms comprises propylene.

32. (Original) The process of claim 31 wherein comonomer is present at 1 to 45 mole%.


33. (Original) The process of claim 20 wherein the polymerization medium of the monomer, comonomers, solvents and diluents comprises from 55-100 wt% propylene monomer; from 0 to 45 wt% of a comonomer mixture comprising at least one comonomer selected from ethylene, but-1-ene, hex-1-ene, 4-methylpent-1-ene, dicyclopentadiene, norbornene, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ -olefins, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ -internal-diolefins, and C<sub>4</sub>-C<sub>2000</sub>  $\alpha,\omega$ -diolefins.

34. (Original) The process of claim 20 wherein the comonomer comprises one or more of ethylene, butene, hexene, or octene.

35. (Original) The process of claim 20 wherein the polymerization system further comprises a bisamide catalyst compound.

36. (Original) The process of claim 20 wherein the polymerization system further comprises a bisimide catalyst compound.

37. (Original) The process of claim 20 wherein the catalyst compound is represented by the formula:





where  $M^1$  is selected from titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum, or tungsten;


$R^1$  and  $R^2$  are identical or different and are selected from hydrogen atoms,  $C_1$ - $C_{10}$  alkyl groups,  $C_1$ - $C_{10}$  alkoxy groups,  $C_6$ - $C_{10}$  aryl groups,  $C_6$ - $C_{10}$  aryloxy groups,  $C_2$ - $C_{10}$  alkenyl groups,  $C_2$ - $C_{40}$  alkenyl groups,  $C_7$ - $C_{40}$  arylalkyl groups,  $C_7$ - $C_{40}$  alkylaryl groups,  $C_8$ - $C_{40}$  arylalkenyl groups, OH groups or halogen atoms; or conjugated dienes that are optionally substituted with one or more hydrocarbyl, tri(hydrocarbyl)silyl groups or hydrocarbyl tri(hydrocarbyl)silylhydrocarbyl groups;

$R^3$ - $R^{12}$  are the same or different and are selected from hydrogen atoms, halogen atoms,  $C_1$ - $C_{10}$  halogenated or unhalogenated alkyl groups,  $C_6$ - $C_{10}$  halogenated or unhalogenated aryl groups,  $C_2$ - $C_{10}$  halogenated or unhalogenated alkenyl groups,  $C_7$ - $C_{40}$  halogenated or unhalogenated arylalkyl groups,  $C_7$ - $C_{40}$  halogenated or unhalogenated alkylaryl groups,  $C_8$ - $C_{40}$  halogenated or unhalogenated arylalkenyl groups,  $-NR'_2$ ,  $-SR'$ ,  $-OR'$ ,  $-OSiR'_3$  or  $-PR'_2$  radicals in which  $R'$  is one of a halogen atom, a  $C_1$ - $C_{10}$  alkyl group, or a  $C_6$ - $C_{10}$  aryl group; or two or more adjacent radicals  $R^5$  to  $R^7$  together with the atoms connecting them can form one or more rings;

$R^{13}$  is selected from



-B(R<sup>14</sup>)-, -Al(R<sup>14</sup>)-, -Ge-, -Sn-, -O-, -S-, -SO-, -SO<sub>2</sub>-, -N(R<sup>14</sup>)-, -CO-, -P(R<sup>14</sup>)- -P(O)(R<sup>14</sup>)-, -B(NR<sup>14</sup>R<sup>15</sup>)- and -B[N(SiR<sup>14</sup>R<sup>15</sup>R<sup>16</sup>)<sub>2</sub>]-, R<sup>14</sup>, R<sup>15</sup> and R<sup>16</sup> are each independently selected from hydrogen, halogen, C<sub>1</sub>-C<sub>20</sub> alkyl groups, C<sub>6</sub>-C<sub>30</sub> aryl groups, C<sub>1</sub>-C<sub>20</sub> alkoxy groups, C<sub>2</sub>-C<sub>20</sub> alkenyl groups, C<sub>7</sub>-C<sub>40</sub> arylalkyl groups, C<sub>8</sub>-C<sub>40</sub> arylalkenyl groups and C<sub>7</sub>-C<sub>40</sub> alkylaryl groups, or R<sup>14</sup> and R<sup>15</sup>, together with the atom(s) connecting them, form a ring; and M<sup>3</sup> is selected from carbon, silicon, germanium and tin, or R<sup>13</sup> is represented by the formula:



wherein R<sup>17</sup> to R<sup>24</sup> are as defined for R<sup>1</sup> and R<sup>2</sup>, or two or more adjacent radicals R<sup>17</sup> to R<sup>24</sup>, including R<sup>20</sup> and R<sup>21</sup>, together with the atoms connecting them form one or more rings; M<sup>2</sup> is carbon, silicon, germanium, or tin.

38. (Original) The process of claim 20 wherein the catalyst compound comprises one or more of:  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride,



$\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,  
dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dimethyl,  
dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,  
dimethylsilylbis(indenyl)hafnium dichloride,  
dimethylsilylbis(indenyl)hafnium dimethyl,  
dimethylsilyl bis(2-methylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methylfluorenyl) zirconium dichloride,  
dimethylsilyl bis(2-methylfluorenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride, and  
dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride dimethyl.

39. (Original) The process claim 20 wherein the catalyst compound comprises two or more of:

$\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride,  
 $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,

1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,  
dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dimethyl,  
dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,  
dimethylsilylbis(indenyl)hafnium dichloride,  
dimethylsilylbis(indenyl)hafnium dimethyl,  
dimethylsilyl bis(2-methylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methylfluorenyl) zirconium dichloride,  
dimethylsilyl bis(2-methylfluorenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride, and  
dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride dimethyl.

40. (Original) The process claim 20 wherein the catalyst compound comprises:

- 1) dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride;
- 2) dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium methyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl;
- 3) 1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride; or

4) 1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl.

41. (Original) The process of claim 20 wherein the activator comprises alumoxane.

42. (Original) The process of claim 20 wherein the activator comprises a non-coordinating anion.

43. (Original) The process of claim 20 wherein the activator comprises one or more of  
trimethylammonium tetraphenylborate,  
tris(perfluorophenyl) borate,  
tris(perfluoronaphthyl) borate,  
triethylammonium tetraphenylborate,  
tripropylammonium tetraphenylborate,  
tri(n-butyl)ammonium tetraphenylborate,  
tri(t-butyl)ammonium tetraphenylborate,  
N,N-dimethylanilinium tetraphenylborate,  
N,N-diethylanilinium tetraphenylborate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,  
trimethylammonium tetrakis(pentafluorophenyl)borate,  
triethylammonium tetrakis(pentafluorophenyl)borate,  
tripropylammonium tetrakis(pentafluorophenyl)borate,  
tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,  
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-diethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate,  
trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,  
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,

dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium)tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
dialkyl ammonium salts such as: di-(i-propyl)ammonium tetrakis(pentafluorophenyl) borate,  
dicyclohexylammonium tetrakis(pentafluorophenyl) borate,  
triphenylphosphonium tetrakis(pentafluorophenyl) borate,  
tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and  
tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate.

44. (Currently Amended) The process of claim 20 wherein the activator comprises N,N-dimethylanilinium tetra(perfluorophenyl)borate and/or triphenylcarbenium tetra(perfluorophenyl)borate.

45. (Currently Amended) The process of claim 20 wherein the polymerization further takes place in a tubular reactor.

46. (Original) The process of claim 45 wherein the tubular reactor has a length-to-diameter ratios of 1:1 to 20:1.

47. (Currently Amended) The process of claim 45 wherein the tubular reactor has a length-to-diameter ratio of 4:1 to 20:1 and the tubular reactor contains up to six different injection positions.

48. (Original) The process of claim 45 wherein the tubular reactor has a length of 100-2000 meters and an internal diameter of less than 10 cm.

49. (Original) The process of claim 45 wherein the tubular reactor is operated in multiple zones.

50. (Currently Amended) The process claim 20 wherein the polymerization further takes place in an autoclave reactor.

51. (Original) The process of claim 50 wherein the autoclave reactor has a length-to-diameter ratios of 1:1 to 20:1.

52. (Original) The process of claim 50 wherein the autoclave reactor has a length-to-diameter ratio of 4:1 to 20:1 and the reactor contains up to six different injection positions.

53. (Original) The process of claim 50 wherein the autoclave reactor is operated in multiple zones.

54. (Currently Amended) The process of claim 50 further comprising ~~wherein the process comprises~~ (a) continuously feeding olefin monomers, catalyst compound, and activator to the autoclave reactor; (b) continuously polymerizing the monomers ~~in a polymerization zone reactor~~ under elevated pressure; (c) continuously removing the polymer/monomer mixture from the reactor; (d) continuously separating monomer from molten polymer; (e) reducing pressure to form a monomer-rich and a polymer-rich phase; and (f) separating monomer from the polymer.

55. (Cancelled)

56. (Currently Amended) The process of claim ~~[[55]]~~ 20 wherein the loop reactor has a diameter of 41 to 61 cm and a length of 100 to 200 meters.

57. (Cancelled)

58. (Currently Amended) The process of claim ~~[[55]]~~ 20 where an in-line pump continuously circulates the polymerization system through the loop reactor.

59. (Currently Amended) The process of claim ~~[[55]]~~ 20 further comprising ~~wherein the process comprises~~ (a) continuously feeding olefin monomers, catalyst compound, and activator to the loop reactor; (b) continuously polymerizing the monomers ~~in a polymerization zone reactor~~ under elevated pressure; (c) continuously removing the polymer/monomer mixture from the reactor; (d) continuously separating monomer from molten polymer; (e) reducing pressure to form a monomer-rich and a polymer-rich phase; and (f) separating monomer from the polymer.

60. (Original) The process of claim 20 wherein the polymerization takes place in multiple reactors.

61. (Cancelled)

62. (Currently amended) The process of claim 60 wherein the polymerization takes places in a tubular reactor and then ~~[[a]]~~ the loop reactor.

63. (Original) The process of claim 20 wherein the residence time is less than 5 minutes.

64-72 (Canceled).

73. (Previously Presented) The process of claim 20 wherein the catalyst compound comprises one or more of:

dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;



9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;

9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-isobutyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl) η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;



9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;



diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-bis-  
trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-bis-  
trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl; and

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl.

74. (Currently amended) A process to polymerize olefins comprising contacting, in a polymerization system, propylene with:

- 1) a metallocene catalyst compound
- 2) an activator,
- 3) optionally comonomer, and
- 4) optionally diluent or solvent,

at a temperature above the cloud point temperature of the polymerization system and a pressure no lower than 10 MPa below the cloud point pressure of the polymerization system and less than 1000 MPa,

where the polymerization system comprises the propylene, any comonomer present, any diluent or solvent present, and the polymer product,

where the propylene is present in the polymerization system at 40 weight % or more, and

where polymerization takes place in a loop reactor operated at pressures of 25 to 30 MPa.

75. (Cancelled)

76. (Original) The process of claim 74 wherein the temperature is between 140 to 180°C.

77. (Cancelled)

78. (Original) The process of claim 74 wherein the pressure of the polymerization system is above the cloud point pressure of the polymerization system.

79-80 (Cancelled).

81. (Original) The process of claim 74 wherein solvent and or diluent is present in the polymerization system at 0 to 25 wt %.



81. (Cancelled)

82. (Original) The process of claim 74 wherein the propylene is present in the polymerization system at 55 wt % or more.

83. (Original) The process of claim 74 wherein the propylene is present in the polymerization system at 75 wt % or more.

84. (Original) The process of claim 74 wherein comonomer is present at 1 to 45 mole%.


85. (Previously Presented) The process of claim 74 wherein the polymerization medium of the monomer, comonomers, solvents and diluents comprises from 55-100 wt% propylene monomer; from 0 to 45 wt% of a comonomer mixture comprising at least one comonomer selected from ethylene, but-1-ene, hex-1-ene, 4-methylpent-1-ene, dicyclopentadiene, norbornene, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ -olefins, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ ,internal-diolefins, and C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ , $\omega$ -diolefins.

86. (Original) The process of claim 74 wherein the comonomer comprises one or more of ethylene, butene, hexene, or octene.

87. (Original) The process of claim 74 wherein the polymerization system further comprises a bisamide catalyst compound.

88. (Original) The process of claim 74 wherein the polymerization system further comprises a bisimide catalyst compound.

89. (Original) The process of claim 74 wherein the catalyst compound is represented by the formula:





where  $M^1$  is selected from titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum, or tungsten;


$R^1$  and  $R^2$  are identical or different and are selected from hydrogen atoms,  $C_1$ - $C_{10}$  alkyl groups,  $C_1$ - $C_{10}$  alkoxy groups,  $C_6$ - $C_{10}$  aryl groups,  $C_6$ - $C_{10}$  aryloxy groups,  $C_2$ - $C_{10}$  alkenyl groups,  $C_2$ - $C_{40}$  alkenyl groups,  $C_7$ - $C_{40}$  arylalkyl groups,  $C_7$ - $C_{40}$  alkylaryl groups,  $C_8$ - $C_{40}$  arylalkenyl groups, OH groups or halogen atoms; or conjugated dienes that are optionally substituted with one or more hydrocarbyl, tri(hydrocarbyl)silyl groups or hydrocarbyl tri(hydrocarbyl)silylhydrocarbyl groups;

$R^3$ - $R^{12}$  are the same or different and are selected from hydrogen atoms, halogen atoms,  $C_1$ - $C_{10}$  halogenated or unhalogenated alkyl groups,  $C_6$ - $C_{10}$  halogenated or unhalogenated aryl groups,  $C_2$ - $C_{10}$  halogenated or unhalogenated alkenyl groups,  $C_7$ - $C_{40}$  halogenated or unhalogenated arylalkyl groups,  $C_7$ - $C_{40}$  halogenated or unhalogenated alkylaryl groups,  $C_8$ - $C_{40}$  halogenated or unhalogenated arylalkenyl groups,  $-NR'_2$ ,  $-SR'$ ,  $-OR'$ ,  $-OSiR'_3$  or  $-PR'_2$  radicals in which  $R'$  is one of a halogen atom, a  $C_1$ - $C_{10}$  alkyl group, or a  $C_6$ - $C_{10}$  aryl group; or two or more adjacent radicals  $R^5$  to  $R^7$  together with the atoms connecting them can form one or more rings;

$R^{13}$  is selected from



-B(R<sup>14</sup>)-, -Al(R<sup>14</sup>)-, -Ge-, -Sn-, -O-, -S-, -SO-, -SO<sub>2</sub>-, -N(R<sup>14</sup>)-, -CO-, -P(R<sup>14</sup>)- -P(O)(R<sup>14</sup>)-, -B(NR<sup>14</sup>R<sup>15</sup>)- and -B[N(SiR<sup>14</sup>R<sup>15</sup>R<sup>16</sup>)<sub>2</sub>]-, R<sup>14</sup>, R<sup>15</sup> and R<sup>16</sup> are each independently selected from hydrogen, halogen, C<sub>1</sub>-C<sub>20</sub> alkyl groups, C<sub>6</sub>-C<sub>30</sub> aryl groups, C<sub>1</sub>-C<sub>20</sub> alkoxy groups, C<sub>2</sub>-C<sub>20</sub> alkenyl groups, C<sub>7</sub>-C<sub>40</sub> arylalkyl groups, C<sub>8</sub>-C<sub>40</sub> arylalkenyl groups and C<sub>7</sub>-C<sub>40</sub> alkylaryl groups, or R<sup>14</sup> and R<sup>15</sup>, together with the atom(s) connecting them, form a ring; and M<sup>3</sup> is selected from carbon, silicon, germanium and tin, or R<sup>13</sup> is represented by the formula:



wherein R<sup>17</sup> to R<sup>24</sup> are as defined for R<sup>1</sup> and R<sup>2</sup>, or two or more adjacent radicals R<sup>17</sup> to R<sup>24</sup>, including R<sup>20</sup> and R<sup>21</sup>, together with the atoms connecting them form one or more rings; M<sup>2</sup> is carbon, silicon, germanium, or tin.

90. (Original) The process of claim 74 wherein the catalyst compound comprises one or more of:

$\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride,  
 $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,  
dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dimethyl,  
dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,  
dimethylsilylbis(indenyl)hafnium dichloride,  
dimethylsilylbis(indenyl)hafnium dimethyl,  
dimethylsilyl bis(2-methylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methylfluorenyl) zirconium dichloride,  
dimethylsilyl bis(2-methylfluorenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride, and  
dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride dimethyl.

91. (Original) The process claim 74 wherein the catalyst compound comprises two or more of:

$\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride,  
 $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl,

1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,

1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,

dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dimethyl,

dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride,

1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,

1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,

dimethylsilylbis(indenyl)hafnium dichloride,

dimethylsilylbis(indenyl)hafnium dimethyl,

dimethylsilyl bis(2-methylindenyl) zirconium dichloride,

dimethylsilyl bis(2-methylindenyl) zirconium dimethyl,

dimethylsilyl bis(2-methylfluorenyl) zirconium dichloride,

dimethylsilyl bis(2-methylfluorenyl) zirconium dimethyl,

dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dichloride,

dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dimethyl,

dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dichloride,

dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dimethyl,

dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dichloride,

dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dimethyl,

dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride, and

dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride dimethyl.

92. (Currently Amended) The process of claim 74 wherein the catalyst compound comprises:

1) dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride;

2) dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium methyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl;

3) 1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-

9-fluorenyl)hafnium dichloride and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride; or

4) 1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl[[,]].

93. (Original) The process of claim 74 wherein the activator comprises alumoxane.

94. (Original) The process of claim 74 wherein the activator comprises a non-coordinating anion.

95. (Original) The process of claim 74 wherein the activator comprises one or more of  
trimethylammonium tetraphenylborate,  
tris(perfluorophenyl) borate,  
tris(perfluoronaphthyl) borate,  
triethylammonium tetraphenylborate,  
tripropylammonium tetraphenylborate,  
tri(n-butyl)ammonium tetraphenylborate,  
tri(t-butyl)ammonium tetraphenylborate,  
N,N-dimethylanilinium tetraphenylborate,  
N,N-diethylanilinium tetraphenylborate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,  
trimethylammonium tetrakis(pentafluorophenyl)borate,  
triethylammonium tetrakis(pentafluorophenyl)borate,  
tripropylammonium tetrakis(pentafluorophenyl)borate,  
tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,  
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-diethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate,  
trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,  
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,

tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium)tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
dialkyl ammonium salts such as: di-(i-propyl)ammonium tetrakis(pentafluorophenyl) borate,  
dicyclohexylammonium tetrakis(pentafluorophenyl) borate,  
triphenylphosphonium tetrakis(pentafluorophenyl) borate,  
tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and  
tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate.

96. (Currently Amended) The process of claim 74 wherein the activator comprises N,N-dimethylanilinium tetra(perfluorophenyl)borate and/or triphenylcarbenium tetra(perfluorophenyl)borate.

97. (Currently Amended) The process of claim 74 wherein the polymerization further takes place in a tubular reactor.

98. (Currently Amended) The process of claim [[74]] 97 wherein the tubular reactor has a length-to-diameter ratios of 1:1 to 20:1.

99. (Currently Amended) The process of claim 74 wherein the polymerization further takes place in a tubular reactor having a length-to-diameter ratio of 4:1 to 20:1 and the tubular reactor contains up to six different injection positions.

100. (Currently Amended) The process of claim 74 wherein the polymerization further takes place in a tubular reactor having a length of 100-2000 meters and an internal diameter of less than 10 cm.

101. (Currently Amended) The process of claim 74 wherein the polymerization further takes place in a tubular reactor operated in multiple zones.

102. (Currently Amended) The process claim 74 wherein the polymerization further takes place in an autoclave reactor.

103. (Currently Amended) The process of claim 74 wherein the polymerization further takes place in an autoclave reactor having a length-to-diameter ratios of 1:1 to 20:1.

104. (Currently amended) The process of claim 74 wherein the polymerization further takes place in an autoclave reactor having a length-to-diameter ratio of 4:1 to 20:1 and the autoclave reactor contains up to six different injection positions.

105. (Currently amended) The process of claim 74 wherein the polymerization further takes place in an autoclave reactor operated in multiple zones.

106. (Currently amended) The process of claim 74 further comprising: ~~wherein the process comprises~~

(a) continuously feeding propylene, catalyst compound, and activator to an autoclave reactor;

(b) continuously polymerizing the monomers in the reactor under elevated pressure;

(c) continuously removing the polymer/monomer mixture from the reactor;

(d) continuously separating monomer from molten polymer;

(e) reducing pressure to form a monomer-rich and a polymer-rich phase; and

(f) separating monomer from the polymer.

107. (Cancelled)

108. (Currently Amended) The process of claim 74 wherein the ~~polymerization takes place in a~~ loop reactor ~~has~~ having a diameter of 41 to 61 cm and a length of 100 to 200 meters.

109. (Cancelled).

110. (Currently amended) The process of claim 74 wherein ~~the polymerization takes place in a~~ loop reactor ~~where~~ an in-line pump continuously circulates the polymerization system through the loop reactor.



111. (Currently amended) The process of claim 74 further comprising: wherein the process comprises

- (a) continuously feeding olefin monomers, catalyst compound, and activator to ~~[[a]]~~ the loop reactor;
- (b) continuously polymerizing the monomers in the reactor under elevated pressure;
- (c) continuously removing the polymer/monomer mixture from the reactor;
- (d) continuously separating monomer from molten polymer;
- (e) reducing pressure to form a monomer-rich and a polymer-rich phase; and
- (f) separating monomer from the polymer.

112. (Original) The process of claim 74 wherein the polymerization takes place in multiple reactors.

113. (Cancelled)

114. (Currently amended) The process of claim ~~[[74]]~~ 112 wherein the polymerization takes place in a tubular reactor and then ~~[[a]]~~ the loop reactor.

115. (Original) The process of claim 74 wherein the residence time is less than 5 minutes.

116. (Original) The process of claim 74 wherein the catalyst compound comprises one or more of:

dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylsiladiyl(2-isobutyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;



dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
dimethylamidoborane(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
dimethylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
dimethylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
dimethylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
dimethylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
dimethylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride  
dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;  
dimethylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;



dimethylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
diisopropylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
diisopropylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-*t*-butylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*n*-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*n*-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*n*-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*n*-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;



bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl; and  
bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl.

117. (Original) The process of claim 116 wherein the activator comprises one or more of trimethylammonium tetraphenylborate, trisperfluorophenyl borate, trisperfluoronaphtyl borate, triethylammonium tetraphenylborate, tripropylammonium tetraphenylborate, tri(n-butyl)ammonium tetraphenylborate, tri(t-butyl)ammonium tetraphenylborate, N,N-dimethylanilinium tetraphenylborate,

N,N-diethylanilinium tetraphenylborate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,  
trimethylammonium tetrakis(pentafluorophenyl)borate,  
triethylammonium tetrakis(pentafluorophenyl)borate,  
tripropylammonium tetrakis(pentafluorophenyl)borate,  
tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,  
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-diethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate,  
trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,  
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium)tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
dialkyl ammonium salts such as: di-(i-propyl)ammonium tetrakis(pentafluorophenyl) borate,  
dicyclohexylammonium tetrakis(pentafluorophenyl) borate,  
triphenylphosphonium tetrakis(pentafluorophenyl) borate,  
tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and  
tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate.

118-157 (Cancelled).

158. (Previously Presented) The process of claim 20 wherein the temperature is 105 to 150°C.
159. (Previously Presented) The process of claim 74 wherein the temperature is 105 to 150°C.
160. (Previously Presented) The process of claim 20 wherein the temperature is 105 to 140°C.
161. (Previously Presented) The process of claim 74 wherein the temperature is 105 to 140°C.

162-165. (Cancelled)

166. (Previously Presented) The process of claim 20 wherein the activator is an alumoxane or a modified alumoxane and the catalyst compound-to-activator molar ratio is from 1:500 to 2:1.

167. (Previously Presented) The process of claim 74 wherein the activator is an alumoxane or a modified alumoxane and the metallocene catalyst compound-to-activator molar ratio is from 1:500 to 2:1.

168. (Currently Amended) The process of claim ~~[[73]]~~ 74 wherein the activator is an alumoxane or a modified alumoxane and the catalyst compound-to-activator molar ratio is from 1:500 to 2:1.

169. (Currently Amended) The process of claim 168 wherein the temperature is 105 to 150°C and the pressure is ~~15 to 350 MPa~~.

170. (Previously Presented) The process of claim 74 wherein the catalyst compound comprises  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride.

171. (Currently Amended) The process of claim 170 wherein the temperature is 105 to 150°C and the pressure is ~~15 to 350 MPa~~.

172. (Previously Presented) The process of claim 170 wherein the activator is an alumoxane or a modified alumoxane and the catalyst compound-to-activator molar ratio is from 1:500 to 2:1.

173. (Currently Amended) The process of claim 172 wherein the temperature is 105 to 150°C and the pressure is ~~15 to 350 MPa~~.

Please add the following new claims:

174. (New) A process to polymerize olefins comprising contacting, in a polymerization system, propylene with:

a metallocene catalyst compound comprising:

dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium  
dichloride and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium

dichloride;

dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium  
methyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl;  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-  
tertiary-butyl-9-fluorenyl)hafnium dichloride and  $\mu$ -dimethyl silylbis(-2-methyl,  
4-phenylindenyl) zirconium dichloride; or

1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-  
tertiary-butyl-9-fluorenyl)hafnium dimethyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-  
phenylindenyl) zirconium dimethyl;  
an activator,  
optionally comonomer, and  
optionally diluent or solvent,

at a temperature above the cloud point temperature of the polymerization system and a  
pressure no lower than 10 MPa below the cloud point pressure of the polymerization system and  
less than 1000 MPa,

where the polymerization system comprises the propylene, any comonomer present, any  
diluent or solvent present, and the polymer product, and

where the propylene is present in the polymerization system at 40 weight % or more.

175. (New) The process of claim 174 wherein the pressure of the polymerization system is less  
than 125 MPa.

176. (New) The process of claim 174 wherein the temperature is between 140 to 180°C.

177. (New) The process of claim 174 wherein the pressure of the polymerization system is less  
than 100 MPa, and the temperature is between 140 to 180°C.

178. (New) The process of claim 174 wherein the pressure of the polymerization system is  
above the cloud point pressure of the polymerization system.

179. (New) The process of claim 174 wherein the pressure of the polymerization system is  
between 15 and 140 MPa.

180. (New) The process of claim 174 wherein the pressure of the polymerization system is between 15 and 50 MPa.

181. (New) The process of claim 174 wherein solvent and or diluent is present in the polymerization system at 0 to 25 wt %.

182. (New) The process of claim 174 wherein solvent and or diluent is present in the polymerization system at 0 to 10 wt %.

183. (New) The process of claim 174 wherein the propylene is present in the polymerization system at 55 wt % or more.

184. (New) The process of claim 174 wherein the propylene is present in the polymerization system at 75 wt % or more.

185. (New) The process of claim 174 wherein comonomer is present at 1 to 45 mole%.

186. (New) The process of claim 174 wherein the polymerization medium of the monomer, comonomers, solvents and diluents comprises from 55-100 wt% propylene monomer; from 0 to 45 wt% of a comonomer mixture comprising at least one comonomer selected from ethylene, but-1-ene, hex-1-ene, 4-methylpent-1-ene, dicyclopentadiene, norbornene, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ -olefins, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ -internal-diolefins, and C<sub>4</sub>-C<sub>2000</sub>  $\alpha,\omega$ -diolefins.

187. (New) The process of claim 174 wherein the comonomer comprises one or more of ethylene, butene, hexene, or octene.

188 (New) The process of claim 174 wherein the activator comprises alumoxane.

189. (New) The process of claim 174 wherein the activator comprises a non-coordinating anion.

190. (New) The process of claim 174 wherein the activator comprises one or more of:

trimethylammonium tetraphenylborate,

tris(perfluorophenyl) borate,

tris(perfluoronaphthyl) borate,

triethylammonium tetraphenylborate,

tripropylammonium tetraphenylborate,

tri(n-butyl)ammonium tetraphenylborate,  
tri(t-butyl)ammonium tetraphenylborate,  
N,N-dimethylanilinium tetraphenylborate,  
N,N-diethylanilinium tetraphenylborate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,  
trimethylammonium tetrakis(pentafluorophenyl)borate,  
triethylammonium tetrakis(pentafluorophenyl)borate,  
tripropylammonium tetrakis(pentafluorophenyl)borate,  
tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,  
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-diethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate,  
trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,  
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium)tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
dialkyl ammonium salts such as: di-(i-propyl)ammonium tetrakis(pentafluorophenyl)  
borate,  
dicyclohexylammonium tetrakis(pentafluorophenyl) borate,  
triphenylphosphonium tetrakis(pentafluorophenyl) borate,  
tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and  
tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate.

191. (New) The process of claim 174 wherein the activator comprises N,N-dimethylanilinium tetra(perfluorophenyl)borate and/or triphenylcarbenium tetra(perfluorophenyl)borate.



192. (New) The process of claim 174 wherein the polymerization takes place in a tubular reactor.

193. (New) The process of claim 174 wherein the tubular reactor has a length-to-diameter ratios of 1:1 to 20:1.

194. (New) The process of claim 174 wherein the polymerization takes place in a tubular reactor having a length-to-diameter ratio of 4:1 to 20:1 and the reactor contains up to six different injection positions.

195. (New) The process of claim 174 wherein the polymerization takes place in a tubular reactor having a length of 100-2000 meters and an internal diameter of less than 10 cm.

196. (New) The process of claim 174 wherein the polymerization takes place in a tubular reactor operated in multiple zones.

197. (New) The process claim 174 wherein the polymerization takes place in an autoclave reactor.

198. (New) The process of claim 174 wherein the polymerization takes place in an autoclave reactor having a length-to-diameter ratios of 1:1 to 20:1.

199. (New) The process of claim 174 wherein the polymerization takes place in an autoclave reactor having a length-to-diameter ratio of 4:1 to 20:1 and the reactor contains up to six different injection positions.

200. (New) The process of claim 174 wherein the polymerization takes place in an autoclave reactor operated in multiple zones.

201. (New) The process of claim 174 wherein the process comprises (a) continuously feeding propylene, catalyst compound, and activator to an autoclave reactor; (b) continuously polymerizing the monomers in the reactor under elevated pressure; (c) continuously removing the polymer/monomer mixture from the reactor; (d) continuously separating monomer from molten polymer; (e) reducing pressure to form a monomer-rich and a polymer-rich phase; and (f)

separating monomer from the polymer.

202. (New) The process of claim 174 wherein the polymerization takes place in a loop reactor having a diameter of 41 to 61 cm and a length of 100 to 200 meters.

203. (New) The process of claim 174 wherein the polymerization takes place in a loop reactor where an in-line pump continuously circulates the polymerization system through the loop reactor.

204. (New) The process of claim 174 wherein the process comprises (a) continuously feeding olefin monomers, catalyst compound, and activator to a loop reactor; (b) continuously polymerizing the monomers in the reactor under elevated pressure; (c) continuously removing the polymer/monomer mixture from the reactor; (d) continuously separating monomer from molten polymer; (e) reducing pressure to form a monomer-rich and a polymer-rich phase; and (f) separating monomer from the polymer.

205. (New) The process of claim 174 wherein the polymerization takes place in multiple reactors.

206. (New) The process of claim 174 wherein the polymerization takes places in a tubular reactor and then an autoclave reactor.

207. (New) The process of claim 174 wherein the polymerization takes places in a tubular reactor and then a loop reactor.

208. (New) The process of claim 174 wherein the residence time is less than 5 minutes.

209. (New) The process of claim 174 wherein the activator comprises one or more of:  
trimethylammonium tetraphenylborate,  
tris(perfluorophenyl) borate,  
tris(perfluoronaphthyl) borate,  
triethylammonium tetraphenylborate,  
tripropylammonium tetraphenylborate,  
tri(n-butyl)ammonium tetraphenylborate,

tri(t-butyl)ammonium tetraphenylborate,  
N,N-dimethylanilinium tetraphenylborate,  
N,N-diethylanilinium tetraphenylborate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,  
trimethylammonium tetrakis(pentafluorophenyl)borate,  
triethylammonium tetrakis(pentafluorophenyl)borate,  
tripropylammonium tetrakis(pentafluorophenyl)borate,  
tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,  
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-diethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate,  
trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,  
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium)tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
dialkyl ammonium salts such as: di-(i-propyl)ammonium tetrakis(pentafluorophenyl) borate,  
dicyclohexylammonium tetrakis(pentafluorophenyl) borate,  
triphenylphosphonium tetrakis(pentafluorophenyl) borate,  
tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and  
tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate.

210. (New) The process of claim 174 where the pressure of the polymerization system is between 10 and 100 MPa and the temperature is between 140 and 190°C.

211. (New) The process of claim 174 where the pressure of the polymerization system is between 10 and 60 MPa.

212. (New) The process of claim 174 wherein the temperature is 105 to 150°C.
213. (New) The process of claim 174 wherein the temperature is 105 to 140°C.
214. (New) The process of claim 174 wherein the pressure is 15 to 350 MPa.
215. (New) The process of claim 174 wherein the pressure is 50 to 200 MPa.
216. (New) The process of claim 174 wherein the activator is an alumoxane or a modified alumoxane and the metallocene catalyst compound-to-activator molar ratio is from 1:500 to 2:1.
217. (New) The process of claim 174 wherein the activator is an alumoxane or a modified alumoxane and the catalyst compound-to-activator molar ratio is from 1:500 to 2:1.
218. (New) The process of claim 217 wherein the temperature is 105 to 150°C and the pressure is 15 to 350 MPa.
219. (New) A process to polymerize olefins comprising:  
    contacting, in a polymerization system, olefin monomers having three or more carbon atoms with:  
        a metallocene catalyst compound comprising:  
            dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride,  
            dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium methyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl, 1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride, or  
            1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl;  
        an activator;

optionally comonomer; and

optionally diluent or solvent,

at a temperature above the cloud point temperature of the polymerization system and a pressure no lower than 10 MPa below the cloud point pressure of the polymerization system and less than 150 MPa,

where the polymerization system comprises the monomers, any comonomer present, any diluent or solvent present, and the polymer product, and

where the olefin monomers are present in the polymerization system at 40 weight % or more.

220. (New) The process of claim 219 wherein the pressure of the polymerization system is less than 125 MPa.

221. (New) The process of claim 219 where the temperature is between 140 to 180°C.

222. (New) The process of claim 219 wherein the pressure of the polymerization system is less than 100 MPa, and the temperature is between 140 to 180°C.

223. (New) The process of claim 219 wherein the pressure of the polymerization system is above the cloud point pressure of the polymerization system.

224. (New) The process of claim 219 wherein the pressure of the polymerization system is between 15 and 140 MPa.

225. (New) The process of claim 219 wherein the pressure of the polymerization system is between 15 and 50 MPa.

226. (New) The process of claim 219 wherein solvent and or diluent is present in the polymerization system at 0 to 25 wt %.

227. (New) The process of claim 219 wherein solvent and or diluent is present in the polymerization system at 0 to 10 wt %.

228. (New) The process of claim 219 wherein the olefin monomers having three or more carbon atoms are present in the polymerization system at 55 wt % or more.

229. (New) The process of claim 219 wherein the olefin monomers having three or more carbon atoms are present in the polymerization system at 75 wt % or more.

230. (New) The process of claim 219 wherein the olefin monomer having three or more carbon atoms comprises propylene.

231. (New) The process of claim 230 wherein comonomer is present at 1 to 45 mole%.

232. (New) The process of claim 219 wherein the polymerization medium of the monomer, comonomers, solvents and diluents comprises from 55-100 wt% propylene monomer; from 0 to 45 wt% of a comonomer mixture comprising at least one comonomer selected from ethylene, but-1-ene, hex-1-ene, 4-methylpent-1-ene, dicyclopentadiene, norbornene, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ -olefins, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ ,internal-diolefins, and C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ , $\omega$ -diolefins.

233. (New) The process of claim 219 wherein the comonomer comprises one or more of ethylene, butene, hexene, or octene.

234. (New) The process of claim 219 wherein the polymerization system further comprises a bisamide catalyst compound.

235. (New) The process of claim 219 wherein the polymerization system further comprises a bisimide catalyst compound.

236. (New) The process of claim 219 wherein the activator comprises alumoxane.

237. (New) The process of claim 219 wherein the activator comprises a non-coordinating anion.

238. (New) The process of claim 219 wherein the activator comprises one or more of trimethylammonium tetrphenylborate,  
tris(perfluorophenyl) borate,  
tris(perfluoronaphthyl) borate,  
triethylammonium tetrphenylborate,

tripropylammonium tetraphenylborate,  
tri(n-butyl)ammonium tetraphenylborate,  
tri(t-butyl)ammonium tetraphenylborate,  
N,N-dimethylanilinium tetraphenylborate,  
N,N-diethylanilinium tetraphenylborate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,  
trimethylammonium tetrakis(pentafluorophenyl)borate,  
triethylammonium tetrakis(pentafluorophenyl)borate,  
tripropylammonium tetrakis(pentafluorophenyl)borate,  
tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,  
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-diethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate,  
trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,  
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium)tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
dialkyl ammonium salts such as: di-(i-propyl)ammonium tetrakis(pentafluorophenyl) borate,  
dicyclohexylammonium tetrakis(pentafluorophenyl) borate,  
triphenylphosphonium tetrakis(pentafluorophenyl) borate,  
tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and  
tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate.

239. (New) The process of claim 219 wherein the activator comprises N,N-dimethylanilinium tetra(perfluorophenyl)borate and/or triphenylcarbenium tetra(perfluorophenyl)borate.

240. (New) The process of claim 219 wherein polymerization takes place in a tubular reactor.

241. (New) The process of claim 240 wherein the tubular reactor has a length-to-diameter ratios of 1:1 to 20:1.

242. (New) The process of claim 240 wherein the tubular reactor has a length-to-diameter ratio of 4:1 to 20:1 and the reactor contains up to six different injection positions.

243. (New) The process of claim 240 wherein the tubular reactor has a length of 100-2000 meters and an internal diameter of less than 10 cm.

244. (New) The process of claim 240 wherein the tubular reactor is operated in multiple zones.

245. (New) The process claim 219 wherein polymerization takes place in an autoclave reactor.

246. (New) The process of claim 245 wherein the autoclave reactor has a length-to-diameter ratios of 1:1 to 20:1.

247. (New) The process of claim 245 wherein the autoclave reactor has a length-to-diameter ratio of 4:1 to 20:1 and the reactor contains up to six different injection positions.

248. (New) The process of claim 245 wherein the autoclave reactor is operated in multiple zones.

249. (New) The process of claim 245 wherein the process comprises (a) continuously feeding olefin monomers, catalyst compound, and activator to the autoclave reactor; (b) continuously polymerizing the monomers under elevated pressure; (c) continuously removing the polymer/monomer mixture from the reactor; (d) continuously separating monomer from molten polymer; (e) reducing pressure to form a monomer-rich and a polymer-rich phase; and (f) separating monomer from the polymer.

250. (New) The process of claim 219 wherein polymerization takes place in a loop reactor.

251. (New) The process of claim 250 wherein the loop reactor has a diameter of 41 to 61 cm and a length of 100 to 200 meters.



252. (New) The process of claim 250 wherein the loop reactor is operated at pressures of 25 to 30 MPa.

253. (New) The process of claim 250 where an in-line pump continuously circulates the polymerization system through the loop reactor.

254. (New) The process of claim 250 wherein the process comprises (a) continuously feeding olefin monomers, catalyst compound, and activator to the loop reactor; (b) continuously polymerizing the monomers under elevated pressure; (c) continuously removing the polymer/monomer mixture from the reactor; (d) continuously separating monomer from molten polymer; (e) reducing pressure to form a monomer-rich and a polymer-rich phase; and (f) separating monomer from the polymer.

255. (New) The process of claim 219 wherein polymerization takes place in multiple reactors.

256. (New) The process of claim 255 wherein the polymerization takes places in a tubular reactor and then an autoclave reactor.

257. (New) The process of claim 255 wherein the polymerization takes places in a tubular reactor and then a loop reactor.

258. (New) The process of claim 219 wherein the residence time is less than 5 minutes.

259. (New) The process of claim 219 wherein the activator comprises one or more of:

trimethylammonium tetraphenylborate,  
tris(perfluorophenyl) borate,  
tris(perfluoronaphthyl) borate,  
triethylammonium tetraphenylborate,  
tripropylammonium tetraphenylborate,  
tri(n-butyl)ammonium tetraphenylborate,  
tri(t-butyl)ammonium tetraphenylborate,  
N,N-dimethylanilinium tetraphenylborate,  
N,N-diethylanilinium tetraphenylborate,

N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,  
trimethylammonium tetrakis(pentafluorophenyl)borate,  
triethylammonium tetrakis(pentafluorophenyl)borate,  
tripropylammonium tetrakis(pentafluorophenyl)borate,  
tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,  
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-diethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate,  
trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,  
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium)tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
dialkyl ammonium salts such as: di-(i-propyl)ammonium tetrakis(pentafluorophenyl) borate,  
dicyclohexylammonium tetrakis(pentafluorophenyl) borate,  
triphenylphosphonium tetrakis(pentafluorophenyl) borate,  
tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and  
tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate.

260. (New) The process of claim 219 where the pressure of the polymerization system is between 10 and 100 MPa and the temperature is between 140 and 190°C.

261. (New) The process of claim 219 where the pressure of the polymerization system is between 10 and 60 MPa.

262. (New) The process of claim 219 wherein the temperature is 105 to 150°C.

263. (New) The process of claim 219 wherein the temperature is 105 to 140°C.

264. (New) The process of claim 219 wherein the pressure is 15 to 350 MPa.

265. (New) The process of claim 219 wherein the pressure is 50 to 200 MPa.

266. (New) The process of claim 219 wherein the activator is an alumoxane or a modified alumoxane and the metallocene catalyst compound-to-activator molar ratio is from 1:500 to 2:1.

267. (New) The process of claim 219 wherein the activator is an alumoxane or a modified alumoxane and the catalyst compound-to-activator molar ratio is from 1:500 to 2:1.

268. (New) The process of claim 267 wherein the temperature is 105 to 150°C and the pressure is 15 to 350 MPa.

269. (New) The process of claim 174 wherein the polymerization system further comprises a bisamide catalyst compound.

270. (New) The process of claim 174 wherein the polymerization system further comprises a bisimide catalyst compound.

271. (New) The process of claim 174 wherein polymerization takes place in a loop reactor.

272. (New) The process of claim 271 wherein the loop reactor is operated at pressures of 25 to 30 MPa.

273. (New) The process of claim 271 where an in-line pump continuously circulates the polymerization system through the loop reactor.

274. (New) The process of claim 74 wherein solvent and or diluent is present in the polymerization system at 0 to 10 wt%.

275. (New) A process to polymerize olefins comprising:

contacting, in a polymerization system, olefin monomers having three or more carbon atoms with:

- 1) a metallocene catalyst compound,
- 2) an activator,

3) optionally comonomer, and  
4) optionally diluent or solvent,  
at a temperature above the cloud point temperature of the polymerization system  
and a pressure no lower than 10 MPa below the cloud point pressure of the  
polymerization system and less than 1000MPa,  
where the polymerization system comprises the monomers, any comonomer present, any  
diluent or solvent present, and the polymer product,  
where the olefin monomers are present in the polymerization system at 40 weight % or  
more;  
where polymerization takes place in a loop reactor;  
continuously feeding olefin monomers, catalyst compound, and activator to the loop  
reactor;  
continuously polymerizing the monomers under elevated pressure;  
continuously removing polymer/monomer mixture from the reactor;  
continuously separating monomer from molten polymer;  
reducing pressure to form a monomer-rich and a polymer-rich phase; and  
separating monomer from the polymer.

276. (New) The process of claim 275 wherein the pressure of the polymerization system is  
above the cloud point pressure of the polymerization system.

277. (New) The process of claim 275 where the temperature is between 140 to 180°C.

278. (New) The process of claim 275 wherein the pressure of the polymerization system is less  
than 125 MPa.

279. (New) The process of claim 275 where the temperature is between 140 to 180°C and the  
pressure is less than 100 MPa.

280. (New) The process of claim 275 wherein solvent and or diluent is present in the  
polymerization system at 0 to 25 wt %.

281. (New) The process of claim 275 wherein solvent and or diluent is present in the polymerization system at 0 to 10 wt %.

282. (New) The process of claim 275 wherein the olefin monomers having three or more carbon atoms are present in the polymerization system at 55 wt % or more.

283. (New) The process of claim 275 wherein the olefin monomers having three or more carbon atoms comprise propylene.

284. (New) The process of claim 275 wherein the olefin monomers having three or more carbon atoms are present in the polymerization system at 75 wt % or more.

285. (New) The process of claim 275 wherein comonomer is present at 1 to 45 mole%.


286. (New) The process of claim 275 wherein the polymerization medium of the monomer, comonomers, solvents and diluents comprises from 55-100 wt% propylene monomer; from 0 to 45 wt% of a comonomer mixture comprising at least one comonomer selected from ethylene, but-1-ene, hex-1-ene, 4-methylpent-1-ene, dicyclopentadiene, norbornene, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ -olefins, C<sub>4</sub>-C<sub>2000</sub>  $\alpha$ -internal-diolefins, and C<sub>4</sub>-C<sub>2000</sub>  $\alpha,\omega$ -diolefins.

287. (New) The process of claim 275 wherein the comonomer comprises one or more of ethylene, butene, hexene, or octene.

288. (New) The process of claim 275 wherein the polymerization system further comprises a bisamide catalyst compound.

289. (New) The process of claim 275 wherein the polymerization system further comprises a bisimide catalyst compound.

290. (New) The process of claim 275 wherein the catalyst compound is represented by the formula:





where  $M^1$  is selected from titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum, or tungsten;


$R^1$  and  $R^2$  are identical or different and are selected from hydrogen atoms,  $C_1$ - $C_{10}$  alkyl groups,  $C_1$ - $C_{10}$  alkoxy groups,  $C_6$ - $C_{10}$  aryl groups,  $C_6$ - $C_{10}$  aryloxy groups,  $C_2$ - $C_{10}$  alkenyl groups,  $C_2$ - $C_{40}$  alkenyl groups,  $C_7$ - $C_{40}$  arylalkyl groups,  $C_7$ - $C_{40}$  alkylaryl groups,  $C_8$ - $C_{40}$  arylalkenyl groups, OH groups or halogen atoms; or conjugated dienes that are optionally substituted with one or more hydrocarbyl, tri(hydrocarbyl)silyl groups or hydrocarbyl tri(hydrocarbyl)silylhydrocarbyl groups;

$R^3$ - $R^{12}$  are the same or different and are selected from hydrogen atoms, halogen atoms,  $C_1$ - $C_{10}$  halogenated or unhalogenated alkyl groups,  $C_6$ - $C_{10}$  halogenated or unhalogenated aryl groups,  $C_2$ - $C_{10}$  halogenated or unhalogenated alkenyl groups,  $C_7$ - $C_{40}$  halogenated or unhalogenated arylalkyl groups,  $C_7$ - $C_{40}$  halogenated or unhalogenated alkylaryl groups,  $C_8$ - $C_{40}$  halogenated or unhalogenated arylalkenyl groups,  $-NR'_2$ ,  $-SR'$ ,  $-OR'$ ,  $-OSiR'_3$  or  $-PR'_2$  radicals in which  $R'$  is one of a halogen atom, a  $C_1$ - $C_{10}$  alkyl group, or a  $C_6$ - $C_{10}$  aryl group; or two or more adjacent radicals  $R^5$  to  $R^7$  together with the atoms connecting them can form one or more rings;

$R^{13}$  is selected from



-B(R<sup>14</sup>)-, -Al(R<sup>14</sup>)-, -Ge-, -Sn-, -O-, -S-, -SO-, -SO<sub>2</sub>-, -N(R<sup>14</sup>)-, -CO-, -P(R<sup>14</sup>)- -P(O)(R<sup>14</sup>)-, -B(NR<sup>14</sup>R<sup>15</sup>)- and -B[N(SiR<sup>14</sup>R<sup>15</sup>R<sup>16</sup>)<sub>2</sub>]-, R<sup>14</sup>, R<sup>15</sup> and R<sup>16</sup> are each independently selected from hydrogen, halogen, C<sub>1</sub>-C<sub>20</sub> alkyl groups, C<sub>6</sub>-C<sub>30</sub> aryl groups, C<sub>1</sub>-C<sub>20</sub> alkoxy groups, C<sub>2</sub>-C<sub>20</sub> alkenyl groups, C<sub>7</sub>-C<sub>40</sub> arylalkyl groups, C<sub>8</sub>-C<sub>40</sub> arylalkenyl groups and C<sub>7</sub>-C<sub>40</sub> alkylaryl groups, or R<sup>14</sup> and R<sup>15</sup>, together with the atom(s) connecting them, form a ring; and M<sup>3</sup> is selected from carbon, silicon, germanium and tin, or R<sup>13</sup> is represented by the formula:



wherein R<sup>17</sup> to R<sup>24</sup> are as defined for R<sup>1</sup> and R<sup>2</sup>, or two or more adjacent radicals R<sup>17</sup> to R<sup>24</sup>, including R<sup>20</sup> and R<sup>21</sup>, together with the atoms connecting them form one or more rings; M<sup>2</sup> is carbon, silicon, germanium, or tin.

291. (New) The process of claim 275 wherein the catalyst compound comprises one or more of:

$\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride,  
 $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,  
dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dimethyl,  
dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,  
1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,  
dimethylsilylbis(indenyl)hafnium dichloride,  
dimethylsilylbis(indenyl)hafnium dimethyl,  
dimethylsilyl bis(2-methylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methylfluorenyl) zirconium dichloride,  
dimethylsilyl bis(2-methylfluorenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dichloride,  
dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dimethyl,  
dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride, and  
dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride dimethyl.

292. (New) The process claim 275 wherein the catalyst compound comprises two or more of:

$\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride,  
 $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl,



1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,

1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,

dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dimethyl,

dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride,

1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dichloride,

1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl,

dimethylsilylbis(indenyl)hafnium dichloride,

dimethylsilylbis(indenyl)hafnium dimethyl,

dimethylsilyl bis(2-methylindenyl) zirconium dichloride,

dimethylsilyl bis(2-methylindenyl) zirconium dimethyl,

dimethylsilyl bis(2-methylfluorenyl) zirconium dichloride,

dimethylsilyl bis(2-methylfluorenyl) zirconium dimethyl,

dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dichloride,

dimethylsilyl bis(2-methyl-5,7-propylindenyl) zirconium dimethyl,

dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dichloride,

dimethylsilyl bis(2-methyl-5-phenylindenyl) zirconium dimethyl,

dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dichloride,

dimethylsilyl bis(2-ethyl-5-phenylindenyl) zirconium dimethyl,

dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride, and

dimethylsilyl bis(2-methyl-5-biphenylindenyl) zirconium dichloride dimethyl.

293. (New) The process claim 275 wherein the catalyst compound comprises:

1) dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium dichloride and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride;

2) dimethylsilyl(tetramethylcyclopentadienyl)(dodecylamido)titanium methyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl;

3) 1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-

fluorenyl)hafnium dichloride and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dichloride; or

4) 1, 1'-bis(4-triethylsilylphenyl)methylene-(cyclopentadienyl)(2,7-di-tertiary-butyl-9-fluorenyl)hafnium dimethyl and  $\mu$ -dimethyl silylbis(-2-methyl, 4-phenylindenyl) zirconium dimethyl.

294. (New) The process of claim 275 wherein the activator comprises alumoxane.

295. (New) The process of claim 275 wherein the activator comprises a non-coordinating anion.

296. (New) The process of claim 275 wherein the activator comprises one or more of  
trimethylammonium tetraphenylborate,  
tris(perfluorophenyl) borate,  
tris(perfluoronaphthyl) borate,  
triethylammonium tetraphenylborate,  
tripropylammonium tetraphenylborate,  
tri(n-butyl)ammonium tetraphenylborate,  
tri(t-butyl)ammonium tetraphenylborate,  
N,N-dimethylanilinium tetraphenylborate,  
N,N-diethylanilinium tetraphenylborate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,  
trimethylammonium tetrakis(pentafluorophenyl)borate,  
triethylammonium tetrakis(pentafluorophenyl)borate,  
tripropylammonium tetrakis(pentafluorophenyl)borate,  
tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,  
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-diethylanilinium tetrakis(pentafluorophenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate,  
trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,  
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,

tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate,  
N,N-dimethyl-(2,4,6-trimethylanilinium)tetrakis-(2,3,4,6-tetrafluorophenyl) borate,  
dialkyl ammonium salts such as: di-(i-propyl)ammonium tetrakis(pentafluorophenyl) borate,  
dicyclohexylammonium tetrakis(pentafluorophenyl) borate,  
triphenylphosphonium tetrakis(pentafluorophenyl) borate,  
tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and  
tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate.

297. (New) The process of claim 275 wherein the activator comprises N,N-dimethylanilinium tetra(perfluorophenyl)borate and/or triphenylcarbenium tetra(perfluorophenyl)borate.

298. (New) The process of claim 275 wherein the loop reactor has a diameter of 41 to 61 cm and a length of 100 to 200 meters.

299. (New) The process of claim 275 where an in-line pump continuously circulates the polymerization system through the loop reactor.

300. (New) The process of claim 275 wherein the polymerization takes place in multiple reactors.

301. (New) The process of claim 275 wherein the polymerization takes places in a tubular reactor and then the loop reactor.

302. (New) The process of claim 275 wherein the residence time is less than 5 minutes.

303. (New) The process of claim 275 wherein the catalyst compound comprises one or more of:  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;

dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;

dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;

9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  
hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dichloride;

dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium  
dimethyl;



9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylsiladiyl(2-ethyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

9-silafluorendiyl(2-methyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

9-silafluorendiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub> hafnium dimethyl;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub> hafnium dimethyl;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-isobutyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di- iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dichloride;  
9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>hafnium dimethyl;  
dimethylsiladiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;  
dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;  
dimethylsiladiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-  
1,3-butadiene;  
dimethylsiladiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-  
1,3-butadiene;  
dimethylsiladiyl(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-  
diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-  
1,3-butadiene;  
dimethylsiladiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-  
diphenyl-1,3-butadiene;  
dimethylsiladiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-  
diphenyl-1,3-butadiene;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl) η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylsiladiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;



9-silafluorendiyl(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

9-silafluorendiyl(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

dimethylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-  
1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-  
diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-  
diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-  
diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-  
diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-  
diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-  
diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

dimethylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> zirconium dimethyl;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;

dimethylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dimethyl;

dimethylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

dimethylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-bis-  
trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-bis-  
trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-bis-  
trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-bis-  
trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-bis-  
trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;



diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium  
dichloride;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-  
butadiene;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-  
1,3-butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-  
1,3-butadiene;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-  
1,3-butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-  
1,3-butadiene;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-*t*-butylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*tert*-butyl, 4-[3',5'-di-*t*-butylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*n*-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-bis- trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*n*-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*tert*-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*n*-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-*n*-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

diisopropylamidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dichloride;  
bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;  
bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>  $\eta^4$ -1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;



bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub> η<sup>4</sup>-1,4-diphenyl-1,3-butadiene;

bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-tbutylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-bis-trifluoromethylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;

bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-iso-propylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-methyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-ethyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-n-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-iso-propyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-n-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-iso-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl;  
bis(trimethylsilyl)amidoborane(2-sec-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl; and  
bis(trimethylsilyl)amidoborane(2-tert-butyl, 4-[3',5'-di-phenylphenyl]indenyl)<sub>2</sub>zirconium dimethyl.

304. (New) A process to polymerize olefins comprising contacting, in a polymerization system, propylene with:

- 1) a metallocene catalyst compound
- 2) an activator,
- 3) optionally comonomer, and
- 4) optionally diluent or solvent,

at a temperature above the cloud point temperature of the polymerization system and a pressure no lower than 10 MPa below the cloud point pressure of the polymerization system and less than 1000 MPa,

where the polymerization system comprises the propylene, any comonomer present, any diluent or solvent present, and the polymer product,

where the propylene is present in the polymerization system at 40 weight % or more;  
where the polymerization takes place in a loop reactor operated at pressures of 25 to 30 MPa; and  
continuously feeding olefin monomers, catalyst compound, and activator to the loop reactor;

continuously polymerizing the monomers in the reactor under pressure of 25 to 30 MPa;  
continuously removing the polymer/monomer mixture from the reactor;  
continuously separating monomer from molten polymer;  
reducing pressure to form a monomer-rich and a polymer-rich phase; and  
separating monomer from the polymer.